# No part of this standard may be reproduced without the prior permission of DIN Deutsches Institut für Normung e.V., Berlin. In case of doubt, the German-language original should be consulted as the authoritative text.

# **Round washers**

for high-strength structural steel bolting

<u>DIN</u> 6916

Scheiben, rund, für HV-Schrauben in Stahlkonstruktionen

Supersedes March 1979 edition.


In keeping with current practice in standards published by the International Organization for Standardization (ISO), a comma has been used throughout as the decimal marker.


### Dimensions in mm

# 1 Scope and field of application

The washers specified in this standard are intended for use in GV and SL structural steel bolting in accordance with DIN 18 800 Part 1, together with DIN 6914 bolts and DIN 6915 hexagon nuts.

### 2 Dimensions





13         M 12         13         13,27         24         23,48         3         3,3         2,7         1,6         1,9         0,5         7,03           17         M 16         17         17,27         30         29,48         4         4,3         3,7         1,6         1,9         1         14,6           21         M 20         21         21,33         37         36,38         4         4,3         3,7         2         2,5         1         19,6           23         M 22         23         23,33         39         38,38         4         4,3         3,7         2         2,5         1         24,3           25         M 24         25         25,33         44         43,38         4         4,3         3,7         2         2,5         1         30,6           28         M 27         28         28,52         50         49         5         5,6         4,4         2,5         3         1         50,2           31         M 30         31         31,62         56         54,8         5         5,6         4,4         2,5         3         1         63,2 <t< th=""><th>Nom- inal size<sup>1</sup>)</th><th>For thread size</th><th>diame  min. =  nominal  size</th><th>, .  </th><th>Extendiament  max. =  nominal  size</th><th>ter, d<sub>2</sub></th><th>Tr Nominal size</th><th>nick ness</th><th>s, <i>h</i></th><th>min. =   nominal size</th><th>max.</th><th>e ≈</th><th>Mass (7,85 kg/dm<sup>3</sup>), in kg per 1000 units</th></t<>	Nom- inal size <sup>1</sup> )	For thread size	diame  min. =  nominal  size	, . 	Extendiament  max. =  nominal  size	ter, d <sub>2</sub>	Tr Nominal size	nick ness	s, <i>h</i>	min. =   nominal size	max.	e ≈	Mass (7,85 kg/dm <sup>3</sup> ), in kg per 1000 units
21         M 20         21         21,33         37         36,38         4         4,3         3,7         2         2,5         1         19,6           23         M 22         23         23,33         39         38,38         4         4,3         3,7         2         2,5         1         24,3           25         M 24         25         25,33         44         43,38         4         4,3         3,7         2         2,5         1         30,6           28         M 27         28         28,52         50         49         5         5,6         4,4         2,5         3         1         50,2           31         M 30         31         31,62         56         54,8         5         5,6         4,4         2,5         3         1         63,2	13	M 12	13	13,27	24	23,48	3	3,3	2,7	1,6	1,9	0,5	7,03
23         M 22         23         23,33         39         38,38         4         4,3         3,7         2         2,5         1         24,3           25         M 24         25         25,33         44         43,38         4         4,3         3,7         2         2,5         1         30,6           28         M 27         28         28,52         50         49         5         5,6         4,4         2,5         3         1         50,2           31         M 30         31         31,62         56         54,8         5         5,6         4,4         2,5         3         1         63,2	17	M 16	17	17,27	30	29,48	4	4,3	3,7	1,6	1,9	1	14,6
25         M 24         25         25,33         44         43,38         4         4,3         3,7         2         2,5         1         30,6           28         M 27         28         28,52         50         49         5         5,6         4,4         2,5         3         1         50,2           31         M 30         31         31,62         56         54,8         5         5,6         4,4         2,5         3         1         63,2	21	M 20	21	21,33	37	36,38	4	4,3	3,7	2	2,5	1	19,6
28     M 27     28     28,52     50     49     5     5,6     4,4     2,5     3     1     50,2       31     M 30     31     31,62     56     54,8     5     5,6     4,4     2,5     3     1     63,2	23	M 22	23	23,33	39	38,38	4	4,3	3,7	2	2,5	1	24,3
31 M30 31 31,62 56 54,8 5 5,6 4,4 2,5 3 1 63,2	25	M 24	25	25,33	44	43,38	4	4,3	3,7	2	2,5	1	30,6
31 M 30 31 31,62 56 54,8 5 5,6 4,4 2,5 3 1 63,2		M 27	28	28,52	50	49	5	5,6	4,4	2,5	3	1	50,2
27 M26 27 2762 66 648 6 66 54 3 35 15 115	31	M 30	31		56	54,8	5	5,6	4,4	2,5	3	1	63,2
31 10130 37 37,02 00 04,0 0,0 0,4 0 0,0 1,0 110	37	M 36	37	37,62	66	64,8	6	6,6	5,4	3	3,5	1,5	115

1) Nominal size is equal to  $d_{1 \text{ min}}$ .

Continued on page 2

### 3 Technical delivery conditions

Mechanical properties	Material	Steel <sup>1</sup> ) quenched and tempered to a hardness from 295 to 350 HV 10.				
p p	As specified in	DIN 17 200				
Limit deviations and	Product grade	A				
geometrical tolerances	As specified in	DIN 522				
Surface finish		Bright. DIN 267 Part 10 shall apply with regard to hot dip galvanizing.				
Acceptance inspection		DIN 522 shall apply with regard to acceptance inspection.				
1) At the manufacturer's di	scretion (e.g. C 45).					

### 4 Designation

Designation of a nominal size 21 washer:

Washer DIN 6916 - 21

# 5 Marking

Washers shall be marked on their bottom side both with the manufacturer's symbol and symbol HV.

### Standards referred to

DIN	267 Part 10	Fasteners; technical delivery conditions; hot-dip galvanized components
DIN	522	Washers; technical delivery conditions
DIN	6914	High-strength hexagon head bolts with large widths across flats for structural steel bolting
DIN	6915	High-strength hexagon nuts with large widths across flats for structural steel bolting
DIN	17 200	Steels for quenching and tempering; technical delivery conditions
DIN	18 800 Part 1	Steel structures; design and construction

### **Previous editions**

DIN 6916: 08.62, 12.70, 03.79.

# Amendments

The following amendments have been made to the March 1979 edition:

- a) Limits of size are now specified.
- b) Use of materials as specified in DIN 17200 that are comparable with C 45 has been permitted.
- c) Washers are now to be quenched and tempered, as opposed to hardened (as specified before).
- d) Washers are now to be hot dip galvanized as specified in DIN 267 Part 10.
- e) A specification regarding marking with the manufacturer's symbol has been included.
- f) The standard has been editorially revised.

# **International Patent Classification**

E 04 B 1/38

F 16 B 43/00